



# PRODUCT TESTING SERVICE

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821

TCNA TEST REPORT NUMBER: TCNA-705-15 PAGE: 1

TEST REQUESTED BY: Cepac Tile

TEST METHOD: Mohs' Scratch Hardness

This test method is used to determine the scratch hardness of a tile surface using the Mohs' hardness scale. A scratch test is performed at each level of hardness to determine the hardness of the surface relative to the Mohs' scale.

TEST SUBJECT MATERIAL: Identified by client as: "Reflections 1x2 REF-121"  
Approximate Size as Received: 1"x2"

TEST DATE: 10/26/2015

## TEST PROCEDURE NOTES:

- Sample prep: None
- Three whole tiles were tested.
- The tiles were tested using a Deluxe Hardness Pick Set from Mineralab, LLC. The following minerals are used as standard:
  - 1 - Talc
  - 2 - Gypsum
  - 3 - Calcite
  - 4 - Fluorite
  - 5 - Apatite
  - 6 - Feldspar
  - 7 - Quartz
  - 8 - Topaz
  - 9 - Corundum
  - 10 - Diamond

## TEST RESULTS:

The Mohs Scratch Hardness was determined to be as follows:

Tile Sample #	Mohs Scratch Hardness
1	7
2	7
3	7

COMMENTS: None

## DISCLAIMER AND LIMITATION OF LIABILITY

This report is provided for the sole use of the client and no one else. It is intended for professional use by a knowledgeable professional. If published by the client, it must be published in full, including this disclaimer and limitation of liability.

This report is not an endorsement, recommendation, approval, certification, or criticism by TCNA of any particular product or its application. TCNA recommends that anyone considering the use or

Testing Services: [testing@tileusa.com](mailto:testing@tileusa.com) Literature Orders: [literature@tileusa.com](mailto:literature@tileusa.com) Web Site: [www.tileusa.com](http://www.tileusa.com)

This report is confidential and has been prepared for the exclusive use of the client. It is not an endorsement, approval, certification, or criticism of any product by TCNA. This report shall not be published in any form without prior written consent from TCNA