



PRODUCT PERFORMANCE TESTING LABORATORY

100 Clemson Research Blvd., Anderson, SC 29625

Phone 864.646.8453 Fax 864.646.2821

Email testing@tcnatile.com Web www.TCNAtile.com

TCNA TEST REPORT NUMBER: TCNA-0642-17

PAGE: 1 OF 3

TEST REQUESTED BY: Cepac Tile

TEST METHOD: Mohs' Scratch Hardness

This test method is used to determine the scratch hardness of a tile surface using the Mohs' hardness scale. A scratch test is performed at each level of hardness to determine the hardness of the surface relative to the Mohs' scale.

TEST SUBJECT MATERIAL: Identified by client as: "Continental Subway COS-7"
Approximate Size as Received: 3"x6"

TEST DATE: 6/27/2017

TEST PROCEDURE NOTES:

- Sample prep: None
- Three whole tiles were tested.
- The tiles were tested using a Deluxe Hardness Pick Set from Mineralab, LLC. The following minerals are used as standard:

1 – Talc	6 – Feldspar
2 – Gypsum	7 – Quartz
3 – Calcite	8 – Topaz
4 – Fluorite	9 – Corundum
5 – Apatite	10 – Diamond

TEST RESULTS:

The Mohs Scratch Hardness was determined to be as follows:

Tile Sample #	Mohs Scratch Hardness
1	7
2	7
3	7

COMMENTS: None