



PRODUCT PERFORMANCE TESTING LABORATORY

100 Clemson Research Blvd., Anderson, SC 29625

Phone 864.646.8453 Fax 864.646.2821

Email testing@tcnatile.com Web www.TCNAtile.com

TCNA TEST REPORT NUMBER: TCNA-0633-17

PAGE: 1 OF 3

TEST REQUESTED BY: Cepac Tile

TEST METHOD: Mohs' Scratch Hardness

This test method is used to determine the scratch hardness of a tile surface using the Mohs' hardness scale. A scratch test is performed at each level of hardness to determine the hardness of the surface relative to the Mohs' scale.

TEST SUBJECT MATERIAL: Identified by client as: "Topkapi TPK-3"
Approximate Size as Received: 2"x3" Irregular shape
tile on 12"x12" mosaic
sheet

TEST DATE: 6/27/2017

TEST PROCEDURE NOTES:

- Sample prep: None
- Three whole tiles were tested.
- The tiles were tested using a Deluxe Hardness Pick Set from Mineralab, LLC. The following minerals are used as standard:

1 - Talc	6 - Feldspar
2 - Gypsum	7 - Quartz
3 - Calcite	8 - Topaz
4 - Fluorite	9 - Corundum
5 - Apatite	10 - Diamond

TEST RESULTS:

The Mohs Scratch Hardness was determined to be as follows:

Tile Sample #	Mohs Scratch Hardness
1	7
2	7
3	7

COMMENTS: None