



PRODUCT TESTING SERVICE

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821

TCNA TEST REPORT NUMBER:

TCNA-077-14

PAGE: 1 OF 1

TEST REQUESTED BY:

Cepac Tile

TEST SUBJECT MATERIAL:

Identified by client as: "PF-04-C"

TEST DATE:

3/4/2014

TEST PROCEDURE:

MOHs Scratch Hardness

-Three whole tiles were tested.

-The tiles were tested using a Deluxe Hardness Pick Set from Mineralab, LLC. The following minerals are used as standard:

- 1 – Talc
- 2 – Gypsum
- 3 – Calcite
- 4 – Fluorite
- 5 – Apatite
- 6 – Feldspar
- 7 – Quartz
- 8 – Topaz
- 9 – Corundum
- 10 – Diamond

TEST RESULTS:

The Mohs Scratch Hardness was determined to be as follows:

Tile Sample #	Mohs Scratch Hardness
1	6
2	6
3	6

Katelyn Simpson
Laboratory Manager

3/20/2014