



PRODUCT TESTING SERVICE

100 Clemson Research Blvd. Anderson, SC 29625 Tel (864) 646-TILE Fax (864) 646-2821

TCNA TEST REPORT NUMBER:

TCNA-077-14

PAGE: 1 OF 1

TEST REQUESTED BY:

Cepac Tile

TEST SUBJECT MATERIAL:

Identified by client as: "RT-142M"

TEST DATE:

3/12/2014

TEST PROCEDURE:

MOHs Scratch Hardness

-Three whole tiles were tested.

-The tiles were tested using a Deluxe Hardness Pick Set from Mineralab, LLC. The following minerals are used as standard:

- 1 - Talc
- 2 - Gypsum
- 3 - Calcite
- 4 - Fluorite
- 5 - Apatite
- 6 - Feldspar
- 7 - Quartz
- 8 - Topaz
- 9 - Corundum
- 10 - Diamond

TEST RESULTS:

The Mohs Scratch Hardness was determined to be as follows:

Tile Sample #	Mohs Scratch Hardness
1	7
2	7
3	7

Katelyn Simpson
Laboratory Manager

3/20/2014

Testing Services: testing@tileusa.com Literature Orders: literature@tileusa.com Web Site: www.tileusa.com

This report is confidential and has been prepared for the exclusive use of the client. It is not an endorsement, approval, certification, or criticism of any product by TCNA. This report shall not be published in any form without prior written consent from TCNA